



ConTec SP-307

DESCRIPTION

ConTec SP-307 combines a swipe agent with an effective mix lubricant and hydration aid. It's unique chemistry creates a low to moderate swipe appearance while its lubrication properties minimize both feed and compaction times. SP-307 is ready to use liquid for use all low slump concrete masonry units. SP-307 improves compaction and density producing higher compressive strength and a less permeable units.

APPLICATION

Use **ConTec SP-307** in all types of manufactured concrete where low to moderate swipe is desired. SP-307 is not a water reducer and should not be utilized as such.

PACKAGING

ConTec NC-537P is available in bulk quantities or packaged in 55 gallon (208 L) drums weighing 490 lbs (222 kg) and 260 gallon (984 L) totes weighing 2390 lbs (1084 kg).

TYPICAL PROPERTIES

Specific Gravity at 77F.....	1.02- 1.04
Viscosity at 77F, cps	75—150
Weight per gallon	8.6
% Volatile matter (NVM(1)) ...	12—17

FEATURES / BENEFITS

- Improves cement particle dispersion and hydration.
- Produces a low to moderate swipe.
- Increases compressive through better compaction and hydration.
- Optimizes material flow which shortens overall machine cycle times.
- Creates more defined edges improving overall appearance.
- Reduces mechanical abrasion in equipment

HANDLING / STORAGE

ConTec SP-307 should be stored at temperatures above 35°F (2°C) Care should be taken to prevent this product from freezing. Should SP-307 freeze, warm till completely liquid then use mechanical agitation to reconstitute.

ADDITION RATES

The recommended dosage is 2-5 fl oz /100 lbs (130-325 mL/100kg) of cement. As with most plasticizers, water content should be monitored to achieve desired appearance. Please consult an ICT representative for further recommendations to determine the proper dosage rate and order of addition for your particular process. Order of addition procedures can vary per facility. Never mix SP-307 with other admixtures before application.

The information contained herein is based on data believed by Innovative Concrete Technology, LLC. to be accurate, but we do not assume any liability for the accuracy of this information. All Materials may present an unknown health and safety hazard. We neither suggest nor guarantee that any hazards mentioned are the only ones that exist. Anyone intending to rely on any recommendation or to use any equipment, technique, or material mentioned should also satisfy himself that he can meet all applicable safety and health standards. Determination of the suitability of any information or product for the use contemplated by any user, the manner of that use is the sole responsibility of the user.

Innovative Concrete Technology, LLC

Two Wall Street – Oxford, NJ 07863 • Ph. 908-453-2737 • Fax 908-453-3634